

TECHNICAL DATASHEET

Marbocote® GRP Mould Sealer

Product Description:

Marbocote® MC SEALER is designed as a mould sealer for glass reinforced polyester (GRP), vinyl ester, epoxy or metal moulds. Marbocote® MC SEALER is an advanced polymeric resin in an organic solvent blend. The resin both seals micro porosity and fills minor scratches on the mould surface. The result is a smooth, high gloss surface primed for Marbocote® top-coat application. Marbocote® MC SEALER is especially recommended for use on new moulds and repaired areas on older moulds.

Product Benefits:

- Efficient mould sealer and primer
- Easy application
- Enhances mould gloss (see application details for appropriate coating technique)
- Low odour
- Minimal mould build-up
- Versatile, can be used on all mould surfaces
- Durable; provides semi-permanent base-coat for mould release agent

Physical Properties:

Appearance	: Clear, colourless liquid
Odour	: Hydrocarbon
Specific Gravity	: 0.76 g/cc
Flash Point	: 24°C
Solvents	: Aliphatic hydrocarbon
Coverage	: 20 - 25m ² / L
Shelf life	: One year
Storage	: Flammable store

See safety data sheet for further details

Note:

The polymeric resin used in Marbocote® MC SEALER reacts with moisture. Please ensure can is resealed after use. Marbocote® MC SEALER is supplied ready to use, no shaking or mixing is required. Do not mix with other products or solvents.

Application:

Please read safety data sheet before use.

If necessary, polish mould to desired level of gloss. Marbocote® MC SEALER should only be applied to clean and dry mould surfaces. If a wax or silicone based release agent has been used previously, or if the mould has been polished, remove all traces of previous product using a solvent based cleaner such as Marbocote® Mould Cleaner. Mould cleaning and Marbocote® MC SEALER application should be performed in a well-ventilated area.

1. Apply Marbocote® MC SEALER to clean, dry cotton cloth.
2. Gently wipe over mould surface covering an area of approximately 0.5m². If a high gloss finish is NOT required, go to Step 4.
3. If a higher gloss finish is desired use a second dry cotton cloth to gently wipe off the wet film. Once dry, move to adjacent area. Vigorous rubbing or polishing is not required.
4. Repeat until mould is completely coated. Ensure each application area overlaps the last to ensure complete coverage.
5. Allow at least 15 minutes to cure between coats.
6. Repeat Steps 1-5 above for a further 2 coats (3 in total).
7. Allow final film to cure for at least 30 minutes at room temperature before applying Marbocote® top-coat. Allowing a longer cure or heat curing (e.g. 15 min at 60°C) will improve film durability.

Top-coat:

Marbocote® MC SEALER can be used a sealer and primer for any Marbocote® top-coat, e.g. 227, 335, 75ECO and TRE45 ECO.

Note: The user will determine the suitability for use of this product. The recommendations / data given above are based on information we believe to be accurate. They are intended to be used only as a guide for selection for end-use evaluation and do not constitute a product specification. Marbocote cannot assume responsibility for results obtained by use of this product as we have no control over end-use applications or handling. Marbocote therefore specifically disclaims any damage or loss of any kind in relation to the use of this product.